

STAYING SAFE AND LOOKING GOOD

STAHL'S® CAD-CUT® REFLECTIVE HEAT TRANSFER MATERIALS

GREAT FOR:

- ▶ *Visibility for Safety Markets*
- ▶ *Trendy Looks*
- ▶ *Reflective Performance*

Whether you're looking to keep your customers safe or deliver some eye-catching designs, reflective heat transfer vinyl is right for you. STAHL'S® has an extensive line of reflective materials for every possible use. No longer just for emergency and construction workers or athletes, reflective is trending on athleisure and streetwear. It's ideal for anyone who wants to stand out, even in the dark.



CAD-CUT® REFLECTPRO

High quality retroreflective performance for safety regulated markets.

- Made with 3M™ Scotchlite™ Reflective
- Use when you need to provide high quality ANSI approved, retroreflective performance for safety regulated markets.
- Ideal for high visibility apparel needs.



CAD-CUT® REFLECTIVE II

Affordable reflective special effects for apparel and accessories.

- Expand your market with a reflective special effect finish for up to 40% less than other reflective materials.
- Reflective effect for added visibility and style on backpacks, jackets, performance wear, uniforms, and more.



CAD-CUT® REFLECTIVE GLITTER

Smooth glitter HTV that features a glossy feel and unique reflective finish that shifts in the light.

- Glossy, reflective finish.
- Smooth glitter texture won't flake off.
- Create trendy designs that get noticed.

Expect the Best from CAD-CUT® Heat Transfer Materials

By the yard or by the roll, you're buying STAHL'S® CAD-CUT® reflective materials from your local Master Distributor, ensuring genuine STAHL'S® products with the fastest delivery and at the best price.



MATERIAL DETAILS

CUTTING GUIDELINES

REFLECTPRO

Cutter	Blade	Force	Offset	Speed
Graphtec	45°	12-14	0	30 cm/s
Roland® DG	45°	130-150g	.25	30 cm/s

REFLECTIVE II

Cutter	Blade	Force	Offset	Speed
Graphtec	45°	11-13	0	25 cm/s
Roland® DG	45°	70-90g	.25	25 cm/s

REFLECTIVE GLITTER

Cutter	Blade	Force	Offset	Speed
Graphtec	45°	13	0	35 cm/s
Roland® DG	45°	120g	.25	30 cm/s

HEAT APPLICATION INSTRUCTIONS

REFLECTPRO

Time: 10-20 seconds
Temp: 325-350°F
Pressure: Firm
Peel: Hot

REFLECTIVE II

Time: 10-12 seconds
Temp: 290°F
Pressure: Medium
Peel: Hot

REFLECTIVE GLITTER

Time: 15 seconds
Temp: 300°F
Pressure: Medium
Peel: Warm


COLORS

REFLECTPRO



Silver 4134 U

REFLECTIVE II



Black Cool Gray 11 C Rainbow Black 4145 C Teal 2178 C Silver 428 U

REFLECTIVE GLITTER



Go online to see the most up-to-date color offerings.